

# Inweld 70S-2

AWS/ASME A5.18 ER70S-2

## Chemical Composition of Inweld 70S-2

Fe	C	Cr	Ni	Mo	Mn	Si	P	S	Ni	V	Ti	Zr	Al
Balance	0.07	0.15	0.15	0.15	0.9- 1.4	0.4- 0.7	0.025	0.035	0.15	0.03	0.05- 0.15	0.02- 0.12	0.05- 0.15

Single values are maximum unless otherwise specified.

## Description and Applications

Inweld 70S-2 is used primarily for single-pass welding of killed, semi-killed, and rimmed steels, but may also be used for some multi-pass applications. Because of the added de-oxidants, Inweld 70S-2 can be used for welding steels that have a rusty or dirty surface, with a possible sacrifice of weld quality depending on the condition of the surface. Typical specifications for these steels are ASTM A36, A285-C, A515-55 and A516-70, which have UNS numbers K02600, K02801, K02001, and K02700, respectively.

## Typical Weld Metal Properties

	<u>AWS Spec</u>
Tensile Strength:	70,000 psi
Yield Strength:	58,000 psi
Elongation:	22%

## Recommended Parameters

GMAW (DC Reverse Polarity) Electrode Positive Spray Transfer

<u>Wire Diameter</u>	<u>Voltage</u>	<u>Amperage</u>	<u>Wire Feed IPM</u>
0.023"	23-27	85-170	360-620
0.030"	24-28	135-230	390-670
0.035"	24-28	165-300	360-520
0.045"	24-30	200-375	210-360

1/16" 24-32 275-500 75-125GTAW (DCSP) 2% Thoriated Tungsten Electrode Negative

<u>Material</u>	<u>Tungsten Dia.</u>	<u>Filler Wire Size</u>	<u>Amperage</u>	<u>Argon (CFH)</u>
1/16"	1/16"	1/16"	100-140	20
3/32"	1/16"	1/16"	100-160	20
1/8"	3/32"	1/16"	125-200	20
3/16"	3/32"	3/32"	150-250	25
1/4"	1/8"	1/8"	150-250	25

**INWELDCORPORATION.COM**

**Pennsylvania**  
3962 Portland Street  
Coplay, PA 18037

**North Carolina**  
1029 S. Marietta St.  
Gastonia, NC 28054

**Texas**  
9300 Lawndale St.  
Houston, TX 77012

**California**  
6201 Coliseum Way, Unit A  
Oakland, CA 94621